

Material Data Sheet

PETG 3D

| | | |
|----------------|-------------|--------------------------------|
| Elastomer | PETG | Polyethylenterephthalat Glycol |
| Hardness | | |
| Printing Speed | up to 200 | mm/s |
| Colour | similar RAL | |
| Remarks | | |

Printing properties

| | | | |
|---------------------|-----------------------------------|------|------------------|
| Nozzle Temperature | 275 ± 10 | °C | |
| Heatbed Temperature | 110 ± 5 | °C | |
| Print speed | up to 200 | mm/s | |
| Skirt height | up to the height of printed parts | | |
| Fan speed | 20-30 | % | depends on parts |

Mechanical properties

| | | | |
|-----------------------------------------------------|-------------------|-----------------|----------------|
| Density | 1,22 | g/cm3 | ISO 1183 |
| MFR 220°C / 10 kg | 22 | g/10min | ISO 1183 |
| MVR 220°C / 10 kg | 20 | cm3/10min | ISO 1183 |
| Moisture Absorption 24 hours (28°C / humidity 37 %) | 0,5 | % | Prusa Polymers |
| Moisture Absorption 7 days (28°C / humidity 37 %) | 1 | % | Prusa Polymers |
| Heat deflection Temperature (0,45 MPa) | 113 | °C | ISO 75 |
| Heat deflection Temperature (1,80 MPa) | 93 | °C | ISO 75 |
| Interlayer adhesion | 21 ± 2 | MPa | Prusa Polymers |
| Mechanical properties of printed samples | Horizontal | Vertical | |
| Tensile Yield Strength (MPa) | MPa | 63 ± 1 | ISO 527-1 |
| Tensile Modulus | GPa | 1,9 ± 0,1 | ISO 527-1 |
| Elongation at Yield Point | % | 5,8 ± 0,3 | ISO 527-1 |
| Flexural strength | MPa | 88 ± 1 | ISO 178 |
| Flexural modulus | GPa | 2,1 ± 0,1 | ISO 178 |
| Deflection at Flex. strength | mm | 11 ± 0,2 | ISO 178 |
| Impact Strength Charpy | kJ/m2 | NB | ISO 179-1 |
| Impact S.Charpy notch | kJ/m2 | 12 ± 1 | ISO 179-1 |

Note

The test results are mean values and represent typical material properties. They are gained under usual laboratory conditions and do not necessarily correspond to results measured on finished goods. The compound information does not release the user from the necessity to conduct his own testing's. Production methods and ingredients are subject to change with regard to technical progress and toxicological regulations

This document does not subject to a revision service

Material Data Sheet

PETG 3D

PC blend Polycarbonate /ABS

- Hohe Schlagzähigkeit bei niedrigen Temperaturen
- Hitzebeständigkeit
- Hohe Festigkeit
- Leichte Verarbeitbarkeit
- Niedrige Schwindung und hohe Dimensionsstabilität
- Einfärб- & bedruckbar

PC blend Polycarbonate /ABS

- High impact strength at low temperatures
- Heat resistance
- High strength
- Easy processability
- Low shrinkage and high dimensional stability
- Colourable & printable

Note

The test results are mean values and represent typical material properties. They are gained under usual laboratory conditions and do not necessarily correspond to results measured on finished goods. The compound information does not release the user from the necessity to conduct his own testing's. Production methods and ingredients are subject to change with regard to technical progress and toxicological regulations